

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-265242

(43)Date of publication of application : 18.09.2002

(51)Int.Cl.

C04B 7/24

(21)Application number : 2001-064517

(71)Applicant : TAIHEIYO CEMENT CORP  
DAIICHI CEMENT CO LTD

(22)Date of filing : 08.03.2001

(72)Inventor : SUGAYA HIDEYUKI  
HONMA KENICHI  
ICHIKAWA MAKIHIKO  
KOIBUCHI KIYOSHI  
YAMAGUCHI HIROYUKI

## (54) CEMENT CLINKER AND CEMENT COMPOSITION

## (57)Abstract:

PROBLEM TO BE SOLVED: To provide a cement clinker which has an improved reduction ratio of compressive strength even in the case of a high phosphor content, and a cement composition produced from the clinker.

SOLUTION: The cement clinker is obtained by burning the raw material for a cement clinker containing waste having a high phosphor content (such as the incineration products of sewerage sludge, incineration ashes of municipal waste and steel making slag), and having a P<sub>2</sub>O<sub>5</sub> content of 0.3 to 2.5 mass%. The clinker has a hydraulic modulus(HM) of 1.8 to 2.15, a silica modulus(SM) of 1.3 to 2.4, and an MgO content of 1.0 to 5.0 mass%. Further, the cement composition is obtained by mixing the cement clinker with gypsum so that the total SO<sub>3</sub> content is controlled to 1.5 to 4.0 mass%, and by pulverizing the mixture/or individually pulverizing the clinker and gypsum each other, and mixing them.

## LEGAL STATUS

[Date of request for examination]

13.06.2005

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]